



Product Technical Data / Product Type: 101/6/10

Absorbency (g/g)

15 Minute Free Swell Capacity (0.9% Saline):	47
15 Minute Free Swell Capacity (DM):	>140
0.3 psi Absorption Under Load (0.9% Saline):	22
0.3 psi Absorption Under Load (DM):	>45

Physical Properties

Colour:	White
Staple Length (mm):	5.8
Moisture Content (%):	10% (Typical)
Count (dtex):	9 (Mean value)
pH (Saline Extract):	5.5 (Mean value)

Other Aspects

Packaging:	Bales, wrapped and sealed in polypropylene. Each labelled to show: <ul style="list-style-type: none"> • Fibre type • Unique bale identification number • Bale weight
------------	---

Additional notes

- All tests are carried out in accordance with Technical Absorbents Standard Test Methods which are available upon request.
- All absorbency specifications are quoted on dry fibre.

Technical Absorbents Ltd.

1 Moody Lane, Great Coates, Grimsby,
North East Lincolnshire, DN31 2SS. United Kingdom

☎ +44 (0)1472 245200 ✉ info@exploreSAF.com

exploreSAF.com

a Technical Absorbents product